

ANALYTICAL REPORT

Client Information

Mid Ocean Brands BV
Wellensiekstraat 2
Ede GLD (NETHERLANDS)

For the attention of Bernadetta Kobluk

Order Information

Order Code:	EFYL24050506
Reception Date:	29-May-2024
Analysis Starting Date:	29-May-2024
Analysis Ending Date:	06-Jun-2024
Overall Conclusion:	Pass

Additional information of the order⁽²⁾

Sample Information

ID	Sample Code	Client Reference ⁽²⁾	Additional Information ⁽²⁾		
A	560-2405-01238	CG1001 / CG1101			
COMPONENT ID	COMPONENT NAME	MATERIAL DESCRIPTION	COLOR	REMARKS	
A1	Blue fabric	Textile	Blue		
A2	White fabric	Textile	White		
A3	Collar fabric	Textile	Blue		
A4	Collar fabric	Textile	White		

SAMPLE PICTURE



CONCLUSION:

TEST PROPERTY	PASS	FAIL	REMARKS
Colour fastness to rubbing ISO 105-X12:2016			
A1			Not applicable
A3			Not applicable
Determination of azo dyes EN ISO 14362-1:2017 Annex F			
A1 & A2	X		
A3 & A4	X		
Lead content in non-metal products CPSC-CH-E1002-08.3			
A1 & A2	X		
A3 & A4	X		

RESULTS

Colour fastness to rubbing

ISO 105-X12:2016

ID	A1	Requirements:	No requirements
Parameter		RESULTS	GUIDELINES
Type of finger		Cylindrical finger	
Conditioning		4h - 20 ± 2°C; 65 ± 4% H.r.	
Test temperature		20.2 °C	
Test humidity		65.3 %	
Staining on dry lengthwise		4-5	
Staining on dry crosswise		4-5	
Staining on wet lengthwise		3	
Staining on wet crosswise		3	
Remarks: Applied force 9 ± 0.2 N Water absorption rate for wet test: Between 95% and 100% Conditioning: At least 4h at 20±2 °C and 65 ±4 % Test conditions: 20±2 °C and 65 ±4 %			
			Analysis Ending Date: 06/06/2024

ID	A3	Requirements:	No requirements
Parameter		RESULTS	GUIDELINES
Type of finger		Cylindrical finger	
Conditioning		4h - 20 ± 2°C; 65 ± 4% H.r.	
Test temperature		20.2 °C	
Test humidity		65.3 %	
Staining on dry crosswise		4-5	
Staining on wet crosswise		3	
Remarks: Applied force 9 ± 0.2 N Water absorption rate for wet test: Between 95% and 100% Conditioning: At least 4h at 20±2 °C and 65 ±4 % Test conditions: 20±2 °C and 65 ±4 % Single direction due to lack of sample.			
			Analysis Ending Date: 06/06/2024

Determination of azo dyes

EN ISO 14362-1:2017 Annex F

ID	A1 & A2	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter		CAS No.	RESULTS	LOQ.	GUIDELINES
4-Aminobiphenyl		92-67-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS 

ID	A1 & A2	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter	CAS No.	RESULTS	LOQ.	GUIDELINES	
Benzidin	92-87-5	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4-Chlorotoluidine	95-69-2	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2-Naphthylamine	91-59-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
p-Chloroaniline	106-47-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Diaminoanisole	615-05-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Diaminodiphenylmethan	101-77-9	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dichlorobenzidine	91-94-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dimethoxybenzidine	119-90-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dimethylbenzidine	119-93-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Diamino-3,3-dimethyl diphenylmethane	838-88-0	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
p-Cresidine	120-71-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Methylene-bis-2- chloroaniline	101-14-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4-Aminophenileter	101-80-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Thioaniline	139-65-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
o-Toluidine	95-53-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Diaminotoluene	95-80-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4,5-Trimethylaniline	137-17-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
o-Anisidine	90-04-0	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Xylidine	95-68-1	<5 mg/kg	5		
2,6-Xylidine	87-62-7	<5 mg/kg	5		
Aniline*	62-53-3	<5 mg/kg	5		
1-4-phenylenediamine*	106-50-3	<5 mg/kg	5		
4-Chloro-o-toludinium chloride *	3165-93-3	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓

ID	A1 & A2	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter		CAS No.	RESULTS	LOQ.	GUIDELINES
2-Naphthylammoniumacetate *		553-00-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
4-Methoxy-m-phenylene Diammonium Sulphate *		39156-41-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
2,4,5-Trimethylaniline hydrochloride *		21436-97-5	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
Remarks: Analytical method technique: GC/MS Sampling procedure: Section 9 EN 14362-1:2017 Evaluation Procedure - Point 10.2 (EN ISO 14362-1:2017) *Parameters not covered by the accreditation scope o-aminoazotoluene and 5-nitro-o-toluidine are further reduced to o-toluidine and 2,4-diaminotoluene. Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline (CAS number 62-53-3) and 1,4 phenyldiamine (CAS-number 106-50-3). Due to detection limits, only aniline may be detected. The presence of these colorants should be tested by EN ISO 14362-3. Conclusion: Amines o-aminoazotoluene and 5-nitro-o-toluidine are further reduced to o-toluidine and 2,4-diaminotoluene. Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline (CAS number 62-53-3) and 1,4 phenyldiamine (CAS-number 106-50-3). Due to detection limits, only aniline may be detected. The presence of these colorants should be tested by EN 14362-3.					
				Analysis Ending Date: 03/06/2024	

ID	A3 & A4	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter	CAS No.	RESULTS	LOQ.	GUIDELINES	
4-Aminobiphenyl	92-67-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
Benzidin	92-87-5	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4-Chlorotoluidine	95-69-2	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2-Naphthylamine	91-59-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
p-Chloroaniline	106-47-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Diaminoanisole	615-05-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Diaminodiphenylmethan	101-77-9	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dichlorobenzidine	91-94-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dimethoxybenzidine	119-90-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
3,3-Dimethylbenzidine	119-93-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Diamino-3,3-dimethyl diphenylmethane	838-88-0	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
p-Cresidine	120-71-8	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Methylene-bis-2- chloroaniline	101-14-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4-Aminophenileter	101-80-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
4,4-Thioaniline	139-65-1	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
o-Toluidine	95-53-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Diaminotoluene	95-80-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4,5-Trimethylaniline	137-17-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
o-Anisidine	90-04-0	<5 mg/kg	5	REACH : < 30 mg/kg PASS	✓
2,4-Xylidine	95-68-1	<5 mg/kg	5		
2,6-Xylidine	87-62-7	<5 mg/kg	5		
Aniline*	62-53-3	<5 mg/kg	5		
1-4-phenylenediamine*	106-50-3	<5 mg/kg	5		

ID	A3 & A4	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter		CAS No.	RESULTS	LOQ.	GUIDELINES
4-Chloro-o-toluidinium chloride *		3165-93-3	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
2-Naphthylammoniumacetate *		553-00-4	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
4-Methoxy-m-phenylene Diammonium Sulphate *		39156-41-7	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
2,4,5-Trimethylaniline hydrochloride *		21436-97-5	<5 mg/kg	5	REACH : < 30 mg/kg PASS ✓
Remarks: Analytical method technique: GC/MS Sampling procedure: Section 9 EN 14362-1:2017 Evaluation Procedure - Point 10.2 (EN ISO 14362-1:2017) *Parameters not covered by the accreditation scope o-aminoazotoluene and 5-nitro-o-toluidine are further reduced to o-toluidine and 2,4-diaminotoluene. Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline (CAS number 62-53-3) and 1,4 phenyldiamine (CAS-number 106-50-3). Due to detection limits, only aniline may be detected. The presence of these colorants should be tested by EN ISO 14362-3. Conclusion: Amines o-aminoazotoluene and 5-nitro-o-toluidine are further reduced to o-toluidine and 2,4-diaminotoluene. Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline (CAS number 62-53-3) and 1,4 phenyldiamine (CAS-number 106-50-3). Due to detection limits, only aniline may be detected. The presence of these colorants should be tested by EN 14362-3.					
				Analysis Ending Date: 03/06/2024	

Lead content in non-metal products
CPSC-CH-E1002-08.3

ID	A1 & A2	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter		CAS No.	RESULTS	LOQ.	GUIDELINES
Lead (Pb)		7439-92-1	<0.0005 %	0.0005	REACH: <0.05 % ✔ PASS
Remarks: Analytical method technique: ICP-MS					
				Analysis Ending Date: 03/06/2024	

ID	A3 & A4	Requirements:	REACH Regulation (EC) No 1907/2006		
Parameter		CAS No.	RESULTS	LOQ.	GUIDELINES
Lead (Pb)		7439-92-1	<0.0005 %	0.0005	REACH: <0.05 % ✔ PASS
Remarks: Analytical method technique: ICP-MS					
				Analysis Ending Date: 03/06/2024	

Signed for and on behalf of Eurofins Textile Testing Spain:

Report electronically validated by



Maria Jesus Martinez Puig
Chemical Lab manager

EXPLANATORY NOTE

- ◆ Test not covered by ENAC accreditation scope
 - Test is subcontracted within Eurofins group and is accredited
 - Test is subcontracted within Eurofins group and is not accredited
 - Test is subcontracted outside Eurofins group and is accredited
 - Test is subcontracted outside Eurofins group and is not accredited
- N/A = Not Applicable

(2) Information provided by the customer. Eurofins Textile Testing Spain S.L.U is not responsible of the information supplied by the costumer and reported as section "Information provided by the costumer*" and is not covered by ENAC accreditation scope.

Eurofins General Sales Terms and Conditions Applied.

Results obtained refer only to samples, products or material received in Laboratory, as described in section "Sample information" and tested in conditions shown in present report.

Test uncertainties not reported are at customer disposal , for those tests in which it is possible to evaluate the test uncertainty.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $k = 2$, which for a normal distribution provides a level of confidence of approximately 95%.

Reproduction of this document is only valid if it is done completely and under the written permission. Any printed version of this document will be considered as a copy.

If you happen to have any comments, please do it by sending email to textile_spain@cpt.eurofinseu.com and referring to this report number.

End Of Report