
Test Report

Report No. : AGC05443230713-001S1

SAMPLE NAME : Crossbody phone holder
MODEL NAME : ML1058, ML1059
APPLICANT : MID OCEAN BRANDS B.V
STANDARD(S) : Please refer to the following page(s).
DATE OF ISSUE : Aug. 02, 2023

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.



Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Applicant : MID OCEAN BRANDS B.V
Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.
Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Crossbody phone holder
Model : ML1058, ML1059
Vendor code : 115628
Country of Origin : CHINA
Country of Destination : EUROPE
Sample Received Date : Jul. 19, 2023
Testing Period : Jul. 19, 2023 to Jul. 31, 2023
Test Requested : Selected test(s) as requested by client.

Test Requested:**Conclusion**

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63
- Lead(Pb) Content

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43
- Aromatic Amines Azodyes (AZO) Content

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 27
- Nickel Release

Pass


- Colour fastness to rubbing

Pass

Approved by: 

Huangguohua

Vice Laboratory Manager

Approved by: 

Liangdan, Jessie.Liang

Technical Director

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

Report Revise Record

Report Version	Issued Date	Valid Version	Notes
/	Jul. 31, 2023	Invalid	Initial release
S1	Aug. 02, 2023	Valid	Add pointer picture

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

The photo of the sample



The photo of AGC05443230713-001S1 is for use only with the original report.

Test Point Description

Test point	Test point description
1-1	Black lanyard
1-2	Blue lanyard
1-3	Metal cap
1-4	Metal sheet
1-5	Metal buckle
1-6	Metal D-buckle
1-7	Metal buckle
1-8	Black oxford cloth fabric (polyester)

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Test Results:

Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63
- Lead(Pb) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-1+1-2	1-3	1-4
Lead(Pb)	mg/kg	500	10	N.D.	15	17
Conclusion				Conformity	Conformity	Conformity

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-5	1-6	1-7
Lead(Pb)	mg/kg	500	10	107	N.D.	17
Conclusion				Conformity	Conformity	Conformity

Test Item(s)	Unit	Limit	MDL	Test Result(s)	
				1-8	
Lead(Pb)	mg/kg	500	10	N.D.	
Conclusion				Conformity	

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-1+1-2

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43
- Aromatic Amines Azodyes (AZO) Content

Test Methods and Equipment: EN ISO 14362-1:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)	
				1-1+1-2	
4-Aminobiphenyl CAS:92-67-1	mg/kg	30	5	N.D.	
Benzidine CAS:92-87-5	mg/kg	30	5	N.D.	
4-Chloro-o-toluidine CAS:95-69-2	mg/kg	30	5	N.D.	
2-Naphthylamine CAS:91-59-8	mg/kg	30	5	N.D.	
o-Aminoazotoluene CAS:97-56-3	mg/kg	30	5	N.D.	
5-Nitro-o-toluidine CAS:99-55-8	mg/kg	30	5	N.D.	
p-Chloroaniline CAS:106-47-8	mg/kg	30	5	N.D.	
4-Methoxy-m-phenylenediamine CAS:615-05-4	mg/kg	30	5	N.D.	

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-1+1-2
4,4'-Diaminodiphenylmethane CAS:101-77-9	mg/kg	30	5	N.D.
3,3'-Dichlorobenzidine CAS:91-94-1	mg/kg	30	5	N.D.
3,3'-Dimethoxybenzidine CAS:119-90-4	mg/kg	30	5	N.D.
3,3'-Dimethylbenzidine CAS:119-93-7	mg/kg	30	5	N.D.
4,4'-Methylenedi-o-toluidine CAS:838-88-0	mg/kg	30	5	N.D.
p-Cresidine CAS:120-71-8	mg/kg	30	5	N.D.
4,4'-Methylenebis[2-chloroaniline] CAS:101-14-4	mg/kg	30	5	N.D.
4,4'-Oxydianiline CAS:101-80-4	mg/kg	30	5	N.D.
4,4'-Thiodianiline CAS:139-65-1	mg/kg	30	5	N.D.
2-Aminotoluene CAS:95-53-4	mg/kg	30	5	N.D.
2,4-Toluyldiamine CAS:95-80-7	mg/kg	30	5	N.D.
2,4,5-Trimethylaniline CAS:137-17-7	mg/kg	30	5	N.D.
o-Anisidine CAS:90-04-0	mg/kg	30	5	N.D.
4-Aminoazobenzene CAS:60-09-3	mg/kg	30	5	N.D.
Conclusion				Conformity

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-1+1-2

Note: 4-aminoazobenzene: The EN ISO 14362-1:2017 or ISO 17234-1:2020 methods will enable further cleavage of 4-aminoazobenzene to aniline and / or 1,4-phenylenediamine. If aniline and / or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

Test Methods and Equipment: ISO 17234-1:2020; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-8
4-Aminobiphenyl CAS:92-67-1	mg/kg	30	5	N.D.
Benzidine CAS:92-87-5	mg/kg	30	5	N.D.
4-Chloro-o-toluidine CAS:95-69-2	mg/kg	30	5	N.D.
2-Naphthylamine CAS:91-59-8	mg/kg	30	5	N.D.

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-8
o-Aminoazotoluene CAS:97-56-3	mg/kg	30	5	N.D.
5-Nitro-o-toluidine CAS:99-55-8	mg/kg	30	5	N.D.
p-Chloroaniline CAS:106-47-8	mg/kg	30	5	N.D.
4-Methoxy-m-phenylenediamine CAS:615-05-4	mg/kg	30	5	N.D.
4,4'-Diaminodiphenylmethane CAS:101-77-9	mg/kg	30	5	N.D.
3,3'-Dichlorobenzidine CAS:91-94-1	mg/kg	30	5	N.D.
3,3'-Dimethoxybenzidine CAS:119-90-4	mg/kg	30	5	N.D.
3,3'-Dimethybenzidine CAS:119-93-7	mg/kg	30	5	N.D.
4,4'-Methylenedi-o-toluidine CAS:838-88-0	mg/kg	30	5	N.D.
p-Cresidine CAS:120-71-8	mg/kg	30	5	N.D.
4,4'-Methylenebis[2-chloroaniline] CAS:101-14-4	mg/kg	30	5	N.D.
4,4'-Oxydianiline CAS:101-80-4	mg/kg	30	5	N.D.
4,4'-Thiodianiline CAS:139-65-1	mg/kg	30	5	N.D.
2-Aminotoluene CAS:95-53-4	mg/kg	30	5	N.D.
2,4-Toluyldiamine CAS:95-80-7	mg/kg	30	5	N.D.
2,4,5-Trimethylaniline CAS:137-17-7	mg/kg	30	5	N.D.
o-Anisidine CAS:90-04-0	mg/kg	30	5	N.D.
4-Aminoazobenzene CAS:60-09-3	mg/kg	30	5	N.D.
Conclusion				Conformity

Note: 4-aminoazobenzene: The EN ISO 14362-1:2017 or ISO 17234-1:2020 methods will enable further cleavage of 4-aminoazobenzene to aniline and / or 1,4-phenylenediamine. If aniline and / or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 27

- Nickel Release

Test Methods and Equipment: EN 1811:2011+A1:2015; ICP-OES

Test Point(s)	Parallel Sample	Unit	Limit	MDL	Test Result(s) Nickel Release	Conclusion
1-3	A	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	Conformity
	B	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
	C	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
1-4	A	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	Conformity
	B	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
	C	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
1-5	A	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	Conformity
	B	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
	C	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
1-6	A	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	Conformity
	B	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
	C	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
1-7	A	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	Conformity
	B	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	
	C	$\mu\text{g}/\text{cm}^2/\text{week}$	0.5	0.05	N.D.	

Limit requirements of Nickel Release

Nickel Release		
Type of sample	Pass	Fail
Article with Nickel release limit of $0.5\mu\text{g}/\text{cm}^2/\text{week}$ (Non-body piercing)	$<0.88\mu\text{g}/\text{cm}^2/\text{week}$	$\geq 0.88\mu\text{g}/\text{cm}^2/\text{week}$
Article with Nickel release limit of $0.2\mu\text{g}/\text{cm}^2/\text{week}$ (Body piercing)	$<0.35\mu\text{g}/\text{cm}^2/\text{week}$	$\geq 0.35\mu\text{g}/\text{cm}^2/\text{week}$

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

- Colour fastness to rubbing

Test Method: ISO 105-X12:2016

Rubbing finger: Cylinder

The time of conditioning as well as the atmospheric conditions during testing: 21.5 °C, 63 %R.H., 4 hrs

The percentage of soak of wet rubbing cloth: 95%~100%

The long direction of the specimen: Endwise/ Crossrange

Test point	Test Result		Conclusion
	Colour fastness to rubbing / (Grade)		
	Dry rubbing	Wet rubbing	
1-1	4-5	4-5	Conformity
1-2	4-5	4-5	Conformity
Limit (Client's Requirement)	≥2-3	≥2-3	/

Test Method: ISO 11640-2018

Friction material: White felt

Friction load: 1000g

The time of conditioning as well as the atmospheric conditions during testing: 21.5 °C, 64 %R.H., 24 hrs

The percentage of soak of wet rubbing cloth: 95%

Test point		Test Result		Conclusion
		Colour fastness to rubbing / (Grade)		
		Dry rubbing	Wet rubbing	
1-8	Change in colour	4-5	4-5	Conformity
	Staining	4-5	4-5	Conformity
Limit (Client's Requirement)		≥2-3	≥2-3	/

Note:


Colour Fastness Grade:

Grade 5 = No Colour Change (Best Grade)


Grade 1 = Colour Change Seriously (Bad Grade)

9 grades in gray sample card: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.

Test Flow Chart of Heavy Metal Content



Test Flow Chart of AZO




Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

Test Flow Chart of Nickel Release



Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Conditions of Issuance of Test Reports

1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the “Company”) solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the “Clients”).
2. Any report issued by Company as a result of this application for testing services (the “Report”) shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.
7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.