

TEST REPORT

Applicant: MID OCEAN BRANDS B.V.
WELLENSIEKSTRAAT 2,
6718 XZ, EDE,
THE NETHERLANDS

Number: HKGH03222669

Date: Feb 27, 2025

Attn: DEREK HUI

Sample and Information provided by customer :
Item Name : **Deck chairs**
Item No. : **MCHA01**
Quantity : 2 pieces
Vendor : 118307
Country of Origin : Poland

For and on behalf of :
Intertek Testing Services HK Ltd.

 

Dorothy M.Y. Lau
Vice President



Page 1 of 6



TEST REPORT

Number : HKGH03222669

Conclusion:

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details :

<u>Requirement</u>	<u>Result</u>
(1) BS EN 581-1:2017 - Outdoor furniture – Seating and table for camping, domestic and contract use – Part 1 General requirements (Test level : Camping use)	Pass
(2) BS EN 581-2:2015/AC:2016 Outdoor furniture – Seating and tables for camping, domestic and contract use – Part 2: Mechanical safety requirements and test methods for seating (Test level : Camping use)	Pass

Decision Rule(s):

When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to Intertek's "Decision Rule Document" and is available on Intertek's website. <https://intertekhk.qrd.by/decision-rule-doc..>

If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Document" is not applicable and indication of "∞" was shown as above table.



Page 2 of 6



TEST REPORT

Number : HKGH03222669

(1) General Safety Requirements for Outdoor Furniture

Test Standard : BS EN 581-1 : 2017, Outdoors furniture - Seating and tables for camping, domestic and contract use - Part 1 General safety requirements.

Number of samples tested : One (1) piece.

Testing level : Camping use.

Initial inspection: No visible damage was found.

Clause	Requirement	Assessment
5.1	General	P
5.2	Tubular components	P
5.3	Shear and squeeze points	
5.3.1	Shear and squeeze points when erecting, adjusting and folding away	P
5.3.2	Shear and squeeze points under the influence of power mechanisms	NA
5.3.3	Shear and squeeze points during use	P

Abbreviation : P = Pass; **F = Fail**; NA = Not Applicable; NT = Not Tested

Date sample received : Feb 07, 2025

Testing period : Feb 07, 2025 to Feb 25, 2025



Page 3 of 6

TEST REPORT

Number : HKGH03222669

(2) Mechanical Safety Requirements for Outdoor Seating Furniture

Test standard : BS EN 581-2:2015/AC:2016 – Outdoor furniture – Seating and tables for camping, domestic and contract use – Part 2: Mechanical safety requirements and test methods for seating.

Number of samples tested : One (1) piece.

Testing parameter : Camping use.

Initial inspection: No visible defects was found.

Per Clause 6.1 / 7.1 in the standard, the general safety requirements shall be fulfilled in accordance with the following table:

Clause per EN 581-1	Requirements	Assessment
5.1	Generals	P
5.2	Tubular components	P
5.3	Shear and squeeze points	P
5.3.1	Shear and squeeze points when erecting, adjusting and folding away	P
5.3.2	Shear and squeeze points under the influence of powered mechanisms	NA
5.3.3	Shear and squeeze points during use	P

Abbreviation : P = Pass; **F** = Fail; NA= Not Applicable; NT = Not Tested

Per Clause 7.2.1 in the standard, the requirements shall be fulfilled during and after testing in accordance with the following table:

Standard / Clause	Tests	Assessment
EN 1728:2012, 6.4	Seat static load and back static load test	P
EN 1728:2012, 6.5	Seat front edge static load	P
EN 1728:2012, 6.17	Combined Seat and back durability test	P
EN 1728:2012, 6.19	Durability test on seating with a multi-position back rest	P
EN 1728:2012, 6.11	Arm rest static load test	NA
EN 1728:2012, 6.20	Arm rest durability test	P
EN 1728:2012, 6.15	Leg forward static load test	P
EN 1728:2012, 6.16	Leg sideways static load test	P
EN 1728:2012, 6.24 (Note 1)	Seat impact test	P
EN 1728:2012, 6.8 (Note 2)	Foot rest static test	NA
EN 1022 (Note 3 & 4)	Forward stability	P
EN 1022 (Note 4)	Rearward stability	P
EN 1022 (Note 3 & 4)	Sideways stability	P
Clause 8	Instruction for use	P
Note (1): The application point shall be at least 100 mm from the front edge. This test shall not be carried out on seating with a seat height > 600 mm.		



TEST REPORT

Number : HKGH03222669

Note (2): This test is carried out only on seating with a seat height > 700 mm.

Note (3): This test is not applicable for seating with a seat height < 200 mm and a mass < 5 kg. The height shall be determined by measuring from the floor to the upper seating area on the geometrical centre of the unloaded seat.

Note (4): In the case of seating which might not fulfill the stability requirements before carrying out any tests, the applicable stability tests may be carried out before starting the sequence of tests specified in this table.

Abbreviation : P = Pass; **F = Fail**; NA= Not Applicable; NT = Not Tested

Date sample received : Feb 07, 2025

Testing period : Feb 07, 2025 to Feb 25, 2025



Page 5 of 6

TEST REPORT

Number : HKGH03222669



End of report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the reports, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



Page 6 of 6

TEST REPORT

Applicant: MID OCEAN BRANDS B.V.
WELLENSIEKSTRAAT 2,
6718 XZ, EDE,
THE NETHERLANDS

Number: HKGH03222691 S1

Date: Mar 06, 2025

Attn: DEREK HUI

Sample and Information provided by customer :

Item Name : **Deck chairs**
Item No. : **YC6503, MCHA01, MCHA02, MCHA03, MO6503**
Quantity : **2 pieces per styles**
Vendor : **118307**
Country of Origin : **Poland**
Date sample received : **Feb 06, 2025**
Testing period : **Feb 06, 2025 to Feb 13, 2025**

For and on behalf of :
Intertek Testing Services HK Ltd.



Dorothy M.Y. Lau
Vice President



Page 1 of 15



TEST REPORT

Number : HKGH03222691 S1

Conclusion:

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details :

<u>Requirement</u>	<u>Result</u>
(1) REACH Regulation (EC) No.1907/2006 , Annex XVII Item 63 & Commission regulation (EU) 2015/628 - Lead content requirement	Pass
(2) BS EN ISO 105-X12:2016 -Colour fastness to rubbing test	Pass
(3) Regulation (EC) No. 1907/2006 on REACH Annex XVII as amended by Commission Regulation (EU) No. 835/2012 and Commission Regulation (EU) 2016/217 - Cadmium content requirement	Pass
(4) REACH Regulation (EC) no. 1907/2006, Annex XVII Items 51 & 52, amendment no. 552/2009 & 2018/2005 - Phthalates content	Pass
(5) REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 Annex XVII Item 50 - Polycyclic aromatic hydrocarbons content	Pass
(6) REACH Regulation (EC) no. 1907/2006, Annex XVII Item 43 & amendment (EC) no. 552/2009 and (EU) no. 2096/2020 - Azocolourants content ∞	Pass
(7) Applicant's requirement - Formaldehyde content	Pass
(8) Regulation (EU) No. 2019/1021 on persistent organic pollutants (POPs) & amendment (EU) no. 2021/277 - Pentachlorophenol (PCP) content	Pass

Decision Rule(s):

When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to Intertek's "Decision Rule Document" and is available on Intertek's website. <https://intertekhk.grd.by/decision-rule-doc..>
If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Document" is not applicable and indication of "∞" was shown as above table.

Note : This is to supersede Report No. HKGH03222691 dated Feb 14, 2025 due to Amending sample description



Page 2 of 15



TEST REPORT

Number : HKGH03222691 S1

(1) Lead (Pb) Content

Test Method : Lead content requirement in Commission regulation (EU) 2015/628 amending Annex XVII item 63 of the REACH regulation (EC) No. 1907/2006, acid digestion was used and total Lead content was determined by inductively coupled argon plasma spectrometry.

Lead Content:

Tested Component	Result in %, w/w	Limit in %, w/w
(1)	ND	0.05
(2/3)	ND	0.05
(4/5/6)	ND	0.05
(7)	ND	0.05
(8)	ND	0.05
(9)	ND	0.05
(10)	ND	0.05
(11)	ND	0.05
(12)	ND	0.05
(13)	ND	0.05
(14)	ND	0.05

ND : Not detected (< 0.002%)

Tested Components:

- (1) Light brown plastic (frame of loungers).
- (2) White fabric with multicolor printings (seat of chair).
- (3) White fabric with multicolor printings (seat of "Where is the limit?" lounge).
- (4) White fabric with multicolor printings (seat of "RACING 23" lounge).
- (5) White fabric with light blue / red printings (seat of flower lounge).
- (6) Light brown webbing (strap of "RACING 23" lounge).
- (7) Pale brown wood (frame of chair, all loungers).
- (8) Gold color metal (round crosshead screw).
- (9) Iridescent plated metal (rivet).
- (10) Iridescent plated metal (washer of rivet).
- (11) Iridescent plated metal (slotted screw).
- (12) Silver color metal (flat crosshead screw).
- (13) Silver color metal (staple).
- (14) Gold color metal (staple).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 11, 2025



TEST REPORT

Number : HKGH03222691 S1

(2) Colour Fastness to Rubbing

Test Standard : BS EN ISO 105-X12:2016 Colour Fastness to Rubbing

<u>Tested Component</u>	<u>Dry</u>	<u>Wet</u>
(1)	4-5	4-5
(2)	4-5	4-5
(3)	4-5	4-5
(4)	4-5	4-5
(5)	4-5	4-5

Remark: Evaluating against ISO Grey Scale for Staining.

Applicant's acceptance ratings :

Dry rubbing: 2-3 or above

Wet rubbing: 2-3 or above

Tested Components:

- (1) White woven with light teal and pink printing (YC6503).
- (2) White woven with blue and dark pink multicolor printing (MCHA01).
- (3) White woven with dark blue and green multicolor printing (MCHA02).
- (4) Beige woven tape.
- (5) White woven with blue multicolor printing (MCHA03).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 11, 2025



Page 4 of 15



TEST REPORT

Number : HKGH03222691 S1

(3) Cadmium (Cd) Content

Test Method : In House method TC008.TP. Acid digestion method was used and total Cadmium content was determined by Inductively Coupled Argon Plasma Spectrometry.

Tested Component	Result in %, w/w	Limit in %, w/w
(1)	ND	0.01

ND : Not detected (< 0.0005%)

The above limit was quoted according to Regulation (EC) No. 1907/2006 on REACH Annex XVII as amended by Commission Regulation (EU) No. 835/2012 and Commission Regulation (EU) 2016/217

Tested Component:

(1) Light brown plastic (frame of loungers).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 11, 2025



Page 5 of 15



TEST REPORT

Number : HKGH03222691 S1

(4) Phthalate Content Test

Test Method : ISO 8124-6 : 2023 method A with internal standard calibration, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Seven Phthalates content:

Compound	Result (% w/w)	Limit (% w/w)
	(1)	
Dibutyl phthalate (DBP)	<0.0100	--
Diethyl hexyl phthalate (DEHP)	<0.0100	--
Benzyl butyl phthalate (BBP)	<0.0100	--
Diisobutyl phthalate (DIBP)	<0.0100	--
Sum of DBP, DEHP, BBP & DIBP	<0.0100	0.1
Diisononyl phthalate (DINP)	<0.0100	--
Di-n-octyl phthalate (DnOP)	<0.0100	--
Diisodecyl phthalate (DIDP)	<0.0100	--
Sum of DINP, DnOP & DIDP	<0.0100	0.1

The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) no. 1907/2006, amendment no. 552/2009 taking into account the (EU) regulation 2018/2005 modifying entry 51 for which the DIBP shall not be placed on the market after 7 July 2020 in toys or childcare articles, individually or in any combination with the first three phthalates which already exist in the entry 51, in a concentration equal to or greater than 0,1 % by weight of the plasticised material.

Tested Component:

(1) Light brown plastic (frame of loungers).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 12, 2025



Page 6 of 15



TEST REPORT

Number : HKGH03222691 S1

(5) Polycyclic Aromatic Hydrocarbons (PAH) Content

Test Method : The document AfPS GS 2019:01 PAK issued by the Federal Institute for Occupational Safety and Health, solvent extraction and determined by Gas Chromatographic - Mass Spectrometry (GC/MS).

Compound	Result (ppm)	Limit (ppm)
	(1)	
Benzo(a)pyrene	<0.20	1
Benzo(e)pyrene	<0.20	1
Benzo(a)anthracene	<0.20	1
Chrysene	<0.20	1
Benzo(b)fluoranthene	<0.20	1
Benzo(j)fluoranthene	<0.20	1
Benzo(k)fluoranthene	<0.20	1
Dibenzo(a,h)anthracene	<0.20	1

The above limit was quoted according to Annex XVII Items 50 of the REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 for polycyclic aromatic hydrocarbons (PAH).

Tested Component:

(1) Light brown plastic (frame of loungers).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 10, 2025



TEST REPORT

Number : HKGH03222691 S1

(6) Detection Of Amines Derived From Azocolourants and Azodyes

Test Method : By extraction on cut sample according to the below listed test method(s), followed by Gas Chromatographic - Mass Spectrometric (GC-MS) analysis and confirmed by High-Performance Liquid Chromatography / Diode Array Detector (HPLC/DAD) analysis.

EN ISO 14362-1 : 2017 for Textile Material

EN ISO 17234-1: 2015 for Leather Material

EN ISO 14362-3 : 2017 & EN ISO 17234-2: 2011 for 4-Aminoazobenzene

Method T:

No.	Forbidden Amine	CAS No.	Result (ppm)		
			(1)	(2)	(3)
1	4-Aminodiphenyl	92-67-1	N	N	N
2	Benzidine	92-87-5	N	N	N
3	4-Chloro-o-toluidine	95-69-2	N	N	N
4	2-Naphthylamine	91-59-8	N	N	N
5	o-Aminoazotoluene	97-56-3	N	N	N
6	2-Amino-4-nitrotoluene	99-55-8	N	N	N
7	p-Chloroaniline	106-47-8	N	N	N
8	2,4-Diaminoanisole	615-05-4	N	N	N
9	4,4'-Diaminodiphenylmethane	101-77-9	N	N	N
10	3,3'-Dichlorobenzidine	91-94-1	N	N	N
11	3,3'-Dimethoxybenzidine	119-90-4	N	N	N
12	3,3'-Dimethylbenzidine	119-93-7	N	N	N
13	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	N	N	N
14	p-Cresidine	120-71-8	N	N	N
15	4,4'-Methylene-bis(2-chloroaniline)	101-14-4	N	N	N
16	4,4'-Oxydianiline	101-80-4	N	N	N
17	4,4'-Thiodianiline	139-65-1	N	N	N
18	o-Toluidine	95-53-4	N	N	N
19	2,4-Toluylenediamine	95-80-7	N	N	N
20	2,4,5-Trimethylaniline	137-17-7	N	N	N
21	o-Anisidine	90-04-0	N	N	N
22	p-Aminoazobenzene	60-09-3	N	N	N



Page 8 of 15



TEST REPORT

Number : HKGH03222691 S1

No.	Forbidden Amine	CAS No.	Result (ppm)
			(4/5)
1	4-Aminodiphenyl	92-67-1	N
2	Benzidine	92-87-5	N
3	4-Chloro-o-toluidine	95-69-2	N
4	2-Naphthylamine	91-59-8	N
5	o-Aminoazotoluene	97-56-3	N
6	2-Amino-4-nitrotoluene	99-55-8	N
7	p-Chloroaniline	106-47-8	N
8	2,4-Diaminoanisole	615-05-4	N
9	4,4'-Diaminodiphenylmethane	101-77-9	N
10	3,3'-Dichlorobenzidine	91-94-1	N
11	3,3'-Dimethoxybenzidine	119-90-4	N
12	3,3'-Dimethylbenzidine	119-93-7	N
13	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	N
14	p-Cresidine	120-71-8	N
15	4,4'-Methylene-bis(2-chloroaniline)	101-14-4	N
16	4,4'-Oxydianiline	101-80-4	N
17	4,4'-Thiodianiline	139-65-1	N
18	o-Toluidine	95-53-4	N
19	2,4-Toluylenediamine	95-80-7	N
20	2,4,5-Trimethylaniline	137-17-7	N
21	o-Anisidine	90-04-0	N
22	p-Aminoazobenzene	60-09-3	N



Page 9 of 15



TEST REPORT

Number : HKGH03222691 S1

Method D:

No.	Forbidden Amine	CAS No.	Result (ppm)		
			(1)	(2)	(3)
1	4-Aminodiphenyl	92-67-1	N	N	N
2	Benzidine	92-87-5	N	N	N
3	4-Chloro-o-toluidine	95-69-2	N	N	N
4	2-Naphthylamine	91-59-8	N	N	N
5	o-Aminoazotoluene	97-56-3	N	N	N
6	2-Amino-4-nitrotoluene	99-55-8	N	N	N
7	p-Chloroaniline	106-47-8	N	N	N
8	2,4-Diaminoanisole	615-05-4	N	N	N
9	4,4'-Diaminodiphenylmethane	101-77-9	N	N	N
10	3,3'-Dichlorobenzidine	91-94-1	N	N	N
11	3,3'-Dimethoxybenzidine	119-90-4	N	N	N
12	3,3'-Dimethylbenzidine	119-93-7	N	N	N
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	N	N	N
14	p-Cresidine	120-71-8	N	N	N
15	4,4'-Methylene-bis(2-chloroaniline)	101-14-4	N	N	N
16	4,4'-Oxydianiline	101-80-4	N	N	N
17	4,4'-Thiodianiline	139-65-1	N	N	N
18	o-Toluidine	95-53-4	N	N	N
19	2,4-Toluylenediamine	95-80-7	N	N	N
20	2,4,5-Trimethylaniline	137-17-7	N	N	N
21	o-Anisidine	90-04-0	N	N	N
22	p-Aminoazobenzene	60-09-3	N	N	N



Page 10 of 15

TEST REPORT

Number : HKGH03222691 S1

No.	Forbidden Amine	CAS No.	Result (ppm)
			(4/5)
1	4-Aminodiphenyl	92-67-1	N
2	Benzidine	92-87-5	N
3	4-Chloro-o-toluidine	95-69-2	N
4	2-Naphthylamine	91-59-8	N
5	o-Aminoazotoluene	97-56-3	N
6	2-Amino-4-nitrotoluene	99-55-8	N
7	p-Chloroaniline	106-47-8	N
8	2,4-Diaminoanisole	615-05-4	N
9	4,4'-Diaminodiphenylmethane	101-77-9	N
10	3,3'-Dichlorobenzidine	91-94-1	N
11	3,3'-Dimethoxybenzidine	119-90-4	N
12	3,3'-Dimethylbenzidine	119-93-7	N
13	3,3'-Dimethyl-4,4'diaminodiphenylmethane	838-88-0	N
14	p-Cresidine	120-71-8	N
15	4,4'-Methylene-bis(2-chloroaniline)	101-14-4	N
16	4,4'-Oxydianiline	101-80-4	N
17	4,4'-Thiodianiline	139-65-1	N
18	o-Toluidine	95-53-4	N
19	2,4-Toluylenediamine	95-80-7	N
20	2,4,5-Trimethylaniline	137-17-7	N
21	o-Anisidine	90-04-0	N
22	p-Aminoazobenzene	60-09-3	N

N = Not detected
Detection limit = 5 ppm
Requirement = 30 ppm (max.)

ppm = parts per million = mg/kg

Method T : Direct buffer extraction as per EN ISO 14362-1 : 2017 Section 10.2
Method D : Colourant extraction with Xylene as per EN ISO 14362-1 : 2017 Section 10.1
Method L : EN ISO 17234-1: 2015

If both methods T and D conducted, final conclusion was based on the highest value of each amine.

- High Performance Liquid Chromatographic (HPLC) analysis was used to confirm any detected amines.
- The test component with p-aminoazobenzene less than detection limit was tested by EN ISO 14362-1 : 2017 for textile material / EN ISO 17234-1: 2015 for leather material.



Page 11 of 15



TEST REPORT

Number : HKGH03222691 S1

Tested Components:

- (1) White fabric with multicolor printings (seat of chair).
- (2) White fabric with multicolor printings (seat of "Where is the limit?" lounge).
- (3) White fabric with multicolor printings (seat of "RACING 23" lounge).
- (4) White fabric with light blue / red printings (seat of flower lounge).
- (5) Light brown webbing (strap of "RACING 23" lounge).

Decision Rule:

∞ : In the case of levels per amine component is equal or smaller than 30 ppm:
According to the analysis as carried out, azo colorants which can release one or more of certain listed amines by cleavage of their azo group/s were not detected. The tested sample/component were in compliance with requirement.

In the case of levels per amine component is greater than 30 ppm:
The analytical result suggests that the commodity submitted has been manufactured or treated using azo colorant/s which can release one or more of certain listed amines by cleavage of their azo group/s at levels greater than 30 ppm. The tested sample/component did not comply the requirement.

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 12, 2025

(7) Formaldehyde Release

Test Method : EN717-3 : 1996 by Flask Method.

Tested Component	Result in ppm	Applicant's requirement in ppm ppm
(1)	<1	80

ppm = parts per million = mg/kg

Tested Component:

- (1) Pale brown wood (frame of chair, all loungers).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 13, 2025



Page 12 of 15



TEST REPORT

Number : HKGH03222691 S1

(8) Pentachlorophenol (PCP) Content

Test Standard : With reference to BVL B 82.02-8:2001 for textiles, EN ISO 17070:2015 for leather, CEN/TR 14823:2003 for wood, paper and paper board, and followed by Gas Chromatographic - Mass Spectrometry (GC-MS) analysis.

Tested Component	Result in ppm	Limit in ppm
(1/2)	<0.5	5
(3)	<0.5	5
(4)	<0.5	5

Detection limit = 0.5 ppm

ppm = parts per million = mg/kg

Tested Components:

- (1) White fabric with multicolor printings (seat of chair).
- (2) White fabric with multicolor printings (seat of "Where is the limit?" lounge).
- (3) Pale brown wood (frame of chair, all loungers).
- (4) White fabric with multicolor printings (seat of "RACING 23" lounge) / White fabric with light blue / red printings (seat of flower lounge) / Light brown webbing (strap of "RACING 23" lounge).

Date sample received : Feb 06, 2025

Test Period : Feb 06, 2025 to Feb 13, 2025



Page 13 of 15

TEST REPORT

Number : HKGH03222691 S1



Page 14 of 15

TEST REPORT

Number : HKGH03222691 S1



End of report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the reports, except when information is provided by the Client or when the Client requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



Page 15 of 15